

# NATIONAL

Furniture with Personality®

Seating Fabric  
Grade 2

## Cathedral



3906 Chartres



3917 Stonehenge



3982 Wells



3924 Belgrade



3907 Florence



3936 Derby



3911 Westminster

Available on Quick Delivery  
Refer to back of card for specifications

# Cathedral

## Seating Fabric Grade 2

### Specifications

Contents	100% Polyester
Width	54"
Repeat	.375" Horizontal .875" Vertical
Construction	128 ends/in. 43 picks/in.
Weight	11.2 oz./lin. yd.
Backing	Acrylic
Finish	None

### Statement of Line

3906	Chartres
3907	Florence
3911	Westminster
3917	Stonehenge
3924	Belgrade
3936	Derby
3982	Wells

### Performance



Abrasion	70,000 Double Rubs (Wyzenbeek - Cotton Duck Abradant)(ASTM D4157)
Light Fastness	Class 4/40 hrs. min. (AATCC 16A)
Color Fastness	Class 4 (ASTM D3597, AATCC 8) Wet Class 4 (ASTM D3597, AATCC 8) Dry
Physical Properties	Class 4 (ASTM D3511) Brush Pill 89 lbs. Warp, 87 lbs. Fill (ASTM D4034) Breaking Strength 12 lbs. Warp, 27 lbs. Fill (ASTM D2262) Tear Strength 77 lbs. Warp, 67 lbs. Fill (ASTM D4034) Seam Slippage 186 lbs. Warp, 208 lbs. Fill (ASTMD 5034) Tensile Strength

### Flammability



Passes	California Tech. Bulletin #117 Section E (CS-191-53) UFAC Class 1
--------	--

### Care

Cleanability	W - Water based cleaners may be used.
--------------	---------------------------------------

Please reference price list for product applications. Product details and other data are subject to change without notice.

We will always ship a satisfactory commercial color match. Due to industry standard dye lot variation, colors may not match exactly. Cut yardage and individual memo samples are available. Contact National Customer Service for pricing and availability.

# NATIONAL

Furniture with Personality®

[www.NationalOfficeFurniture.com](http://www.NationalOfficeFurniture.com)

1205 Kimball Boulevard Jasper, IN 47549  
800.482.1717, Fax 812.482.8800  
©Kimball International, Inc. 2006  
Printed in the USA  
Form No. NSCCAT Ver. 09  
A Unit of Kimball International

Due to variations in the configuration, setting, and calibration of various output devices, the digital image colors shown here may vary from actual samples.