

NATIONAL

Furniture with Personality®

Fossil

Seating Fabric
Grade 3



30304 Impression



30305 Shadow



30302 Footprint



30303 Trace



30301 Element



30306 Fragment

Available on Quick Delivery
Refer to back of card for specifications

Fossil

Seating Fabric Grade 3

Specifications

Pattern #	30300
Contents	68% Pre-Consumer Recycled Polyester, 32% Cotton
Width	58.25"
Repeat	15 in./Horizontal 19.8 in./Vertical
Construction	160 ends/in. 72 picks/in.
Weight	Approx. 0.86 lbs./lin. yd.
Backing	Light Acrylic
Finish	Stain Repellant

Statement of Line

30301	Element
30302	Footprint
30303	Trace
30304	Impression
30305	Shadow
30306	Fragment

Performance



Abrasion	Heavy Duty - 60,000 Cycles (Wyzenbeek - Cotton Duck Abradant)(ASTM D4157-02)
Light Fastness	Class 4/40 hrs. min. (AATCC 16)
Color Fastness	Class 3 (AATCC 8) Wet Class 4 (AATCC 8) Dry
Physical Properties	Class 5 (ASTM D3511-02) Brush Pill 100 lbs. Warp, 90 lbs. Fill (ASTM D5034-95) Breaking Strength 23 lbs. Warp, 31 lbs. Fill (ASTM D2261-96) Tear Strength 60 lbs. Warp, 62 lbs. Fill (ASTM D434-95) Seam Slippage


Flammability



Passes	California Tech. Bulletin #117 Section E Class 1
Passes	UFAC Class 1

Care

Cleanability	S - Solvent based cleaners may be used.
--------------	---



To give you a better idea of how this fabric will work for you, the pattern is illustrated here. (Shown at 25%)

Please reference price list for product applications. Product details and other data are subject to change without notice.

We will always ship a satisfactory commercial color match. Due to industry standard dye lot variation, colors may not match exactly. Cut yardage and individual memo samples are available. Contact National Customer Service for pricing and availability.

NATIONAL

Furniture with Personality®

www.NationalOfficeFurniture.com

1205 Kimball Boulevard Jasper, IN 47549
800.482.1717, Fax 812.482.8800
©Kimball International, Inc. 2007
Printed in the USA
Form No. NSCFOS
A Unit of Kimball International

Due to variations in the configuration, setting, and calibration of various output devices, the digital image colors shown here may vary from actual samples.